



GVM TEST HOUSE
AND RESEARCH CENTRE PVT. LTD.

23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



ISO 9001:2015 Certified

TESTING | TRAINING | AUDITING

Test Order Ref: GVM/PAINT/06276-2-2/09/2024

Date of Receipt: 16.09.2024

Date: 04.10.2024

Page No. 1 of 1

GRASIM INDUSTRIES LIMITED (BIRLA PAINT DIVISION)

Taloja-R & D Lab & Pilot Plant, Grasim Industries Limited,
Plot No. 1&1-A/1, Aditya Birla Science & Technology,
Company Pvt. Ltd., Raigad, 410208

TEST REPORT ON SCUFF RESISTANCE ON PAPER PANEL

Source of Sample : Sample Supplied by the Customer
No. of Product tested : 04 (Four Only)
Customer's Reference : PO No. 4900014763 dt.03.09.2024
Condition of Sample : Satisfactory
Lab Reference Number : 2024/SEP/06276-2-2
Period of Test : 03.10.2024 to 03.10.2024
Test Method # : In House Developed Method

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results			
			Birla Opus One Pure Elegance #	Asian Paints Royale Luxury Emulsion #	Lewis Berger Silk Glamour #	Kansai Nerolac Impressions HD #
1	Scuff Resistance on Paper Panel	Visual	L* Initial: 97.59 L* Final: 97.58 ΔL : 0.01	L* Initial: 96.91 L* Final: 94.81 ΔL : 2.1	L* Initial: 96.93 L* Final: 94.61 ΔL : 2.32	L* Initial: 96.01 L* Final: 93.77 ΔL : 2.24

As furnished by the customer.

Remarks - The Lower ΔL value represents the better scuff resistance property.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of lab.
 3. Any correction invalidates this report.

For **GVM TEST HOUSE AND RESEARCH CENTRE PVT. LTD.**



DINESH BURDE
[Signature]
Authorised Signatory



Regd. Office:

402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.