



GVM TEST HOUSE
AND RESEARCH CENTRE PVT. LTD.

23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



TESTING | TRAINING | AUDITING

Test Order Ref: GVM/PAINT/06276-6-1/09/2024

Date of Receipt: 16.09.2024

Date: 04.10.2024

Page No. 1 of 1

GRASIM INDUSTRIES LIMITED (BIRLA PAINT DIVISION)

Taloja-R & D Lab & Pilot Plant, Grasim Industries Limited,
Plot No. 1&1-A/1, Aditya Birla Science & Technology,
Company Pvt. Ltd., Raigad, 410208

TEST REPORT ON SHEEN (GLOSS) VALUES

Source of Sample : Sample Supplied by the Customer
No. of Product tested : 04 (Four Only)
Customer's Reference : PO No. 4900014763 dt.03.09.2024
Condition of Sample : Satisfactory
Lab Reference Number : 2024/SEP/06276-6-1
Period of Test : 03.10.2024 to 03.10.2024
Test Method # : ASTM D 523-2014

TEST RESULTS:

S. N.	Test Conducted	Test Results			
		Birla Opus One Pure Elegance #	Asian Paints Royale Luxury Emulsion #	Lewis Berger Silk Glamour #	Kansai Nerolac Impressions HD #
1	Sheen (Gloss) Value	GH at 60° : 34.3 GH at 85° : 70.1	GH at 60° : 14.4 GH at 85° : 44.6	GH at 60° : 14.5 GH at 85° : 44.5	GH at 60° : 11.8 GH at 85° : 55.9

As furnished by the customer.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of lab.
 3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE PVT. LTD.



DINESH BURDE
[Signature]
Authorised Signatory



Regd. Office:

402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.