



GVM TEST HOUSE
AND RESEARCH CENTRE

23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



ISO 9001:2015 Certified

TESTING | TRAINING | AUDITING

Test Order Ref: GVM/PRIMER/05241-3/04/2024

Date of Receipt :18.04.2024

Date: 30.04.2024

Page No. 1 of 1

GRASIM INDUSTRIES LTD.

P.O. Birlagram, Nagda-456331, District Ujjain,
Madhya Pradesh, India

TEST REPORT ON BITUMEN PRIMER

Source of Sample : Sample supplied by the customer.
Number of samples Tested : 01 (One only).
Customer's Reference : PO No.- 4900004436, dt. -15.04.2024
Lab Reference Number : 2024/APR/05241-3
Condition of sample : Satisfactory
Sample Identification # : Birla Opus Prime APS1 (Solvent Based Bitumen Primer)
Period of Test : 20.04.2024 To 29.04.2024


TEST RESULTS:


S. N.	Test Conducted	Unit	Test Results	Test Method
1	Solid Content	%	55.82	ASTM D 1644: 2001
2	Distillation fractions, percent by volume of the primer -225 °C	%	46	IS 1213: 2020
3	Distillation fractions, percent by volume of the primer -360 °C	%	52	IS 1213: 2020
4	Flash Point by Pensky Martens closed Cup	°C	48	IS 1209: 2021
5	Water Content	%	Nil	IS 1211: 2022
6	Test on residue from distillation up to 360°C:			
a	Ductility, 27°C,	cm	39	IS 1208: 1978
b	Penetration at 25°C, 100 g, 5 sec	1/100 cm	46	IS 1203: 2022
c	Solubility in Trichloroethylene	%	99	IS 1216: 2023


As furnished by the customer.

Note: 1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.

For GVM TEST HOUSE AND RESEARCH CENTRE


GVM TEST HOUSE
AND RESEARCH CENTRE

DINESH BURDE

Authorised Signatory



Regd. Office:

402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.

GSTIN: 27BPBPB4090Q1ZM